

Appl. No. : 10/019,753
Filed : March 5, 2002

AMENDMENTS TO THE SPECIFICATION

Please correct the heading at page 54, line 1 as follows:

COMPARATIVE EXAMPLE 10

Please correct Table 2 on page 57 as follows:



RECEIVED
NOV 16 2003
U.S. TRADEMARK OFFICE
TC 1700

Table 2

| item | unit | Comparative Example 10 | Polymer A | Polymer B | Comparative Example 1 |
|-----------------------|--------------|------------------------|-----------------------|-----------------------|-----------------------|
| | | | Polymer A | Polymer B | Polymer A |
| Molecular weight (Mw) | g/mol | 2200 | 2000000 | 7500 | 200000 |
| Mixing ratio | % by weight | 40 | 60 | 95 | 5 |
| Antioxidant E | % by weight | 0 | 0 | 0 | 0 |
| Silicone amount D | % by weight | 0 | 0 | 0 | 0 |
| Fluidity (MI) | g/10 minutes | 13 | 12 | 12 | 12 |
| Water absorption | % | 0.10 | 0.08 | 0.08 | 0.08 |
| Heat resistance (Tg) | °C | 121 | 142 | 142 | 142 |
| Relative permittivity | - | 2.3 | 2.3 | 2.3 | 2.3 |
| Bending strength | Mpa | 80 | 48 | 48 | 48 |
| Transparency | % | 85 | 85 | 85 | 85 |
| Birefringence | - | 5×10^{-5} | Could not be measured | Could not be measured | Could not be measured |
| Change in hue | - | 0.28 | 0.29 | 0.29 | 0.29 |